BEST AVAILABLE COPY

- 35. (New) The printable film according to claim 33, wherein the substrate is selected from the group consisting of polymer films, polyolefin films, papers, synthetic papers, woven fabrics, nonwoven fabrics, ceramic sheets, metallic fiber sheets, metallized sheets (film), metallic foils, metallic plates, and multilayer composite sheets formed by combination of said materials.
- 36. (New) The printable film according to claim 35, wherein the substrate is an oriented polypropylene film.
- 37. (New) The printable film according to claim 33, wherein the water-dispersible polymer consists essentially of a homopolymer of (meth)acrylic acid or alkyl (meth)acrylate, the alkyl radical having 1 to 10 carbon atoms, or a copolymer of two or more of said monomers or optionally of other vinylic or allylic compounds.
- 38. (New) The printable film according to claim 33, wherein the water dispersible polymer is a urethane or urethane acrylate polymer.
- 39. (New) The printable film according to claim 33, wherein said surface layer further comprises a cross-linking agent in an amount of from 1 to 5% by weight of the water dispersible polymer.
- 40. (New) The printable film according to claim 33, further comprising, between said substrate and said surface layer(s), a primer layer.
- 41. (New) The printable film according to claim 33, wherein only one face is coated with a surface layer and wherein the reverse face of the substrate is covered with a pressure-sensitive adhesive layer.